

TECHNICAL DATA SHEET

Customer:		Date: 20. SEP. 2021
Technical Data :		
Test	Test Method	Specification
Crystallization point, °C, (min.)	ASTM D - 1493	130.8
Color of the molten material, APHA, (max.)	ASTM D - 3366	< 20
Color of the molten material after heat treatment, APHA, (max.)	ASTM D - 3366	40
Free acidity as Phthalic acid, percent by mass, (max.)	IS 5158 A- 4	0.01
Maleic Anhydride (%w/w)	GC	< 0.04
Other impurities (as Benzoic & Phthalide) percent by mass,(max.) (%w/w)	GC	< 0.05
Appearance	Visual	White Flakes
Phthalic Anhydride (%w/w)	GC	> 99.9

Application:

- Alkyd resins for paints and varnishes. □ Plasticizers for PVC □ Unsaturated Polyester Resins.
- Dye intermediate, Pigments...

Packing: □ 25 Kgs net PP bags